

SOFT TOUCH CLEAR BOPP 22 μ m



EMULSION ACRYLIC LAM



Description

Clear lamination film with soft touch. Velvet soft touch feeling. Ideal for label and packaging printing protection.

Facestock

Clear BOPP with Soft Touch Top Coating

Caliper (μ m) ISO 534 22 (\pm 5%)

Adhesive

Emulsion Acrylic

Caliper (μ m) 8 (\pm 1)

Initial Tack (N/in) PSTC-106 \leq 10

180° Peel Adhesion (N/in) ISO-29862 \geq 3.5

Holding (hours) ISO-29863 \geq 10

Tensile Strength (N/in) PSTC-131 \geq 65

E Value % PSTC-131 100 - 200

Laminate Temperature ($^{\circ}$ C) 10 to 50

Working Temperature ($^{\circ}$ C) -10 to 60

Storage Information

Must be stored in temperature of 23 (\pm 2) $^{\circ}$ C and humidity 50 (\pm 5) %.